

Axxanol™ 33CD-HF

Technical Data Sheet

ZERUST®/EXCOR® Axxanol™ 33CD-HF is a high-flash solvent-based temporary rust preventative coating that dries-to-touch, eliminating oily surfaces that attract dust and other contaminants. Use Axxanol™ 33CD-HF when a high-flash point temporary rust preventative is needed to safely protect metal components, machined and cast parts, engines, molds, and more for up to 6 months[‡] during shipment, storage, and work-in-progress.

During drying, the solvent completely evaporates, leaving behind a safe, high-flash, dry-to-touch rust preventative coating. As a result, Axxanol™ 33CD-HF coated and dried parts are safe to handle, and end users do not need to wear personal protective equipment such as a respirator, mask, or safety glasses. However, we recommend using clean gloves without lint or talc to keep metals free of contaminants. After application and allowing metals to completely dry, place them into ZERUST® Vapor Corrosion Inhibitor (VCI) film packaging products for a more robust solution that protects for years[‡] during indoor storage or challenging shipping conditions, such as ocean freight. Axxanol™ 33CD-HF does not intentionally contain barium or heavy metals and complies with Global Automotive Declarable Substance, TSCA, RoHS, and REACH SVHC requirements.

For over 50 years, beginning with the invention of Vapor Corrosion Inhibiting (VCI) film packaging, ZERUST® has led the market in quality corrosion solution products. We are dedicated to providing expert corrosion management services and broadening the range of corrosion solutions for our customers. In addition, ZERUST® users have access to on-site support from ZERUST®/EXCOR® representatives in more than 70 countries. As a result, our customers have peace of mind when they choose ZERUST® for corrosion control management.

Typical Properties

Appearance	Light yellow solvent liquid dries to a dry-to-touch film.
Substrates	Multimetal protection
Coverage*	4075 ft ² (379 m ²) per gal
Wet film thickness (WFT)*	≈ 0.39 mil (10 µm)
VOC content EPA Method 24	6.58 lb/g (789 g/L)
Flashpoint ASTM D93	143°F (62°C)
Kinematic viscosity	≈ 1.4 cSt @ 104°F (40°C)

*The theoretical coverage estimates, based on the stated wet film thicknesses (WFT), should only be used as a guide. These estimates were generated based on internal lab measurements of product coating on flat, smooth 1010 steel stock. Actual coverage data will vary in actual use based on the method of application, type of equipment used, part geometry, surface roughness, drain-off time, drag-out rate, evaporative loss, etc.

This data sheet provides general guidelines for operation, application, and removal. Please contact your ZERUST®/EXCOR® account representative for more specific recommendations on your particular operation and conditions.

Operating Summary

- Ready-to-use solvent-based rust preventative liquid.
- Typical application temperature: 50 – 110°F (10 – 43°C) in most operations.
- See Safety Data Sheet (SDS) section 7 for safe handling recommendations.

Application Technologies

- Can be used in immersion, brush, or spray processes.
- To prevent water contamination of the Axxanol™ 33CD-HF solution, a dewatering step is recommended. Contact your dedicated ZERUST®/EXCOR® account representative for more specific recommendations on your particular operation and conditions.

Product Removal

- Axxanol™ 33CD-HF can be removed from the metal surface with the use of a compatible ZERUST® AxxaWash™ product, commercial alkaline, or solvent cleaner.

Product Control

- Spray application: do not reuse collected product from spray booths or drip pans.
- Immersion application: for extended dip tank use, particular analysis and viscosity checks are recommended. Please contact your dedicated ZERUST®/EXCOR® account representative for detailed information.
- Brush-on application: use a natural bristle brush. Decant into a smaller container. Do not reuse product. Do not contaminate the original product container with the brush.

Scan QR for more



product information
and photos

Availability

ZERUST®/EXCOR® Axxanol™ 33CD-HF is sold as a ready-to-use liquid product. Contact your ZERUST®/EXCOR® representative for ordering information.

Part Number	Quantity*
350-M-00076PL	5 Gal (19 L) Pail
350-M-00076DR	55 Gal (208 L) Drum

*Product sold in US customary units. Metric units approximate.

Protection Info‡

Indoor (unpackaged)‡	Up to 6 months‡
Indoor (w/ ZERUST® VCI packaging)‡	For years‡
Outdoor‡	Not recommended
Humidity ASTM D1748	Up to 600 hours
Salt spray ASTM B117	Up to 4 hours
Compatible with packaging	Yes

Storage

- Store in a cool, dry place and away from sunlight in the original packaging.
- Optimal storage temperature is 50 – 90°F (10 – 32°C) for up to 2 years from the date of shipment.
- Reseal or close the container cap after each use.

Disposal

- Dispose of in accordance with local, national, and international regulations.

Precautions

- Not intended as a permanent coating.
- Always mix well before use.
- Avoid placing metal surfaces in direct contact with wood or cardboard (sources of moisture and acid).
- Wear personal protective equipment as stipulated in the Safety Data Sheet (SDS).
- Refer to SDS for more safety information.

‡ DECLARATION

Corrosion protection claims are based on Northern Technologies International Corporation (NTIC) internal laboratory testing performed under controlled parameters on contaminant-free substrates. Real-world application corrosion protection duration on different substrates will vary and depends on factors such as, but not limited to, the application or use, environmental / storage conditions, surface cleanliness, type of substrates, and coating thickness (where applicable). The use of the term "Up to" in reference to time is defined as any time duration from zero up to a specified time frame, but in no event beyond the specified time frame. The use of the term "for years" is based on NTIC's experience with its products but is in no way guaranteed. The use of the term "Up to" in reference to volume is defined as any volume from zero up to a specified volume but in no event beyond the specified volume of protection. It is the customer's / user's obligation to evaluate product performance, corrosion protection duration, safety, and suitability for intended use within the scope advised in the data sheet and to comply with all applicable laws and regulations. **LIMITED WARRANTY/Disclaimer** Warranty is limited to the replacement of a product that fails to meet specifications. For full warranty and disclaimer information, visit www.zerust.com/warranty.

©2013-2026 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor Tab®, EXCOR®, Flange Saver®, ICB®, ICT®, Natur-VCI®, NTI®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, 沽乐特, Z-PAK® and the Color "Yellow". ABRIGO®, UNICO®, ICB®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.